

RARALKYD SO-4758 XL-PT

FEATURES

Excellent gloss and hardness in stoving enamels
Excellent yellowing resistance in nitro cellulose lacquer
Excellent hardness and flexibility and have very high compatibility with the solvent in use

APPLICATION

Industrial stoving enamels
Clear and pigmented cellulose nitrate lacquer for furniture and motorcars
PU system light color

CHARACTERISTICS

Oil Length	31.4%
Clarity	Clear
Solvent	Xylene
Oil Type	COFA/PalmKernel
Solid Content (% by wt)	75 +/- 1%
Viscosity (Gardner Scale@25°C)	>Z8
Acid Value	<15 mg KOH/g
OH Value (on solids)	8.3 - 8.4 mg KOH/g
Color (Gardner)	4 max

SOLUBILITY DATA

White Spirit	Insoluble
N-Butanol	Insoluble
Xylene	Soluble
N-Butyl Acetate	Soluble
Methyl Ethyl Ketone	Soluble

DELIVERY FORM DETAILS

Supplied as 75% in Xylene packed in mild steel drums (Net. weight 200KG)

SHELF LIFE

Minimum 12 months when stored under standard storage conditions

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.