

## RARALKYD SO-16010 XL

### FEATURES

- Extremely fast dry
- Chain stopped
- Excellent salt spray resistance

### APPLICATIONS

- Corrosion resistance primers
- Excellent isolating varnish and wire enamels
- Automotive refinishing enamels
- Air drying and stoving finishes
- Road Marking paints
- 2K Polyurethan for wood finish

### CHARACTERISTICS

• Oil %	33%
• Phthalic anhydride %	30%
• Solvent	Xylene
• Oil type	Soya bean oil
• Solid Content	60 +/- 2%
• Viscosity Gardner @25°C @60% XL	Z5-Z6
• Viscosity Gardner @25°C @50% XL	W-X
• Viscosity CP @25°C @50% XL	1070-1290
• OH Content	3.9%
• Acid Value mg KOH/gm solid	12 max
• Color Gardner	6 max

### SOLUBILITY DATA

Aliphatic hydrocarbon	Insoluble
Aromatic	Soluble
Chlorinated	Limited
Ketones	Soluble
Alcohols	Insoluble
Esters	Soluble
Glycol-Ethers	Soluble

#### DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRRESIN.COM

## COMPATIBILITY DATA

Medium oil alkyd	Incompatible
Short oil Alkyd	Compatible
Rosin maleate	Compatible
Zinc white	Limited
Red lead	Incompatible
NC	Compatible
Stand oil	Compatible
Isocyanate	Limited
Urea/Melamine resins	Compatible
Chlorinated rubber	Compatible

## DELIVERY FORM DETAILS

It's available at 60% Xylene

## STORAGE

RARALKYD SO-16010 XL Should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures between 5°C and 30°C Exposure to sun shine should be avoided.

## SHELF LIFE

Under the above mentioned storage conditions the stability of RARALKYD SO-16010 XL will be 12 months ex-work

### DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: [info@rarresin.com](mailto:info@rarresin.com)

[WWW.RARRESIN.COM](http://WWW.RARRESIN.COM)