

RARALKYD SO-37090 XL

FEATURES

- High yellowing resistance
- Very High viscosity
- Excellent adhesion & Good Gloss
- Good Hardness & Adhesion
- Good mechanical performance

APPLICATIONS

- Non yellowing baking enamels
- Tin plate varnishes
- High quality clear & pigmented NC lacquers for furniture & motor cars
- General purpose stoving enamels
- Polyurethane finishes

CHARACTERISTICS

• Oil %	31%
• Phthalic anhydride %	45%
• Solvent	Xylene
• Oil type	Coconut fatty acid
• Solid Content	70 +/- 2%
• Viscosity Gardner @25°C @60% XL	approx. Z5
• Viscosity CP @25°C @60% XL	approx. 9700
• OH Content	4%
• Acid Value mg KOH/gm solid	8 max
• Color Gardner	2 max

SOLUBILITY DATA

Aliphatic hydrocarbon	Insoluble
Aromatic	Soluble
Chlorinated	Insoluble
Ketones	Soluble
Alcohols	Limited
Esters	Soluble
Glycol-Ethers	Soluble

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

COMPATIBILITY DATA

Zinc white	Incompatible
Red lead	Incompatible
NC	Compatible
Chlorinated rubber	Incompatible
Stand oil	Incompatible
Isocyanate	Compatible
Urea/Melamine resins	Compatible

DELIVERY FORM DETAILS

It's available at 70% Xylene

STORAGE

RARALKYD SO-37090 XL Should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures between 5°C and 30°C Exposure to sun shine should be avoided.

SHELF LIFE

Under the above mentioned storage conditions the stability of RARALKYD SO-37090 XL will be 12 months ex-work

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRRESIN.COM