

## RARAALKYD SO-1555 XL

### FEATURES

High scratching resistance  
Good sanding and hardness properties in coordination with flexible resin and proper catalyst  
Good clarity for light wood veneer

### APPLICATION

Used for PU sealer with every high transparency and adhesion

### CHARACTERISTICS

Oil length	30%
Clarity	Clear
Solvent	Xylene
Oil type	SOFA
Solid Content (%by wt)	55 +/- 1%
Viscosity (Gardner Scale @ 25°C)	Z2 - Z4
Acid value	<15mg KOH/g
OH value (on solids)	3.5 - 3.6mg KOH/g
Color (Gardner)	4 max

### SOLUBILITY DATA

Aromatic - Esters	Soluble
Aliphatic	Insoluble
Miniral Spirits	Limited
Esters	Soluble
Ketones	Soluble
Alcohols	Limited

### DELIVERY FORM DETAILS

Supplied as 55% in Xylene packed in Mild steel drums (Net. weight 200KG)

### SHELF LIFE

Minimum 12 months when stored under standard storage conditions

**DISCLAIMER:**

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.