

RARAALKYD SO-1706 XL

FEATURES

Fast drying and easy to handle in PU system sealer with selected isocyanides
 Good sanding properties
 For spray and deeping system. Suggested for quick dry

APPLICATION

Used for sealer grades
 Can be blended with SO-5605 XL for topcoat usage

CHARACTERISTICS

Oil Length	27%
Clarity	Clear
Solvent	Toluene
Oil Type	Soya Fatty Acids
Solid Content (% by wt)	70 +/- 1%
Viscosity (Gardner Scale@25°C)	>Z6
Acid Value	<15mg KOH/g
OH Value (on solids)	4.0 - 4.1 mg KOH/g
Color (Gardner)	6 max

SOLUBILITY DATA

Hydrocarbons	Xylene/Toluene Soluble
Miniral Spirits	Limited
Ketons	Soluble
Esters	Soluble
Alcohols	Limited

DELIVERY FORM DETAILS

Supplied as 70% in Xylene packed in mild steel drums (Net. weight 200KG)

SHELF LIFE

Minimum 12 months when stored under standard storage conditions

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.