

RARALKYD SO-1707 TL

FEATURES

Very Fast drying and easy to handle
Very Good Sanding Properties

APPLICATION

Used for sealer grades
Can be blended with SO-5605 XL for topcoat usage.

CHARACTERISTICS

| | |
|--------------------------------|--------------------|
| Oil Length | 27% |
| Clarity | Clear |
| Solvent | Toluene |
| Oil Type | Soya Fatty Acids |
| Solid Content (% by wt) | 70 +/- 1% |
| Viscosity (Gardner Scale@25°C) | >Z6 |
| Acid Value | <15mg KOH/g |
| OH Value (on solids) | 4.0 - 4.1 mg KOH/g |
| Color (Gardner) | 6 max |

SOLUBILITY DATA

| | |
|-----------------|------------------------|
| Hydrocarbons | Xylene/Toluene Soluble |
| Miniral Spirits | Limited |
| Ketons | Soluble |
| Esters | Soluble |
| Alcohols | Limited |

DELIVERY FORM DETAILS

Supplied as 70% in Xylene packed in mild steel drums (Net. weight 200KG)

SHELF LIFE

Minimum 12 months when stored under standard storage conditions

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.