

## RARALKYD SO-2604 XL

### FEATURES

Fast A/D with good hardness and yellowing resistance  
Good forced drying with amino acid

### APPLICATION

Air drying cum stoving enamels  
Primer/undercoats  
Topcoat for machineries / equipment  
Industrial dipping enamel

### CHARACTERISTICS

Oil Length	37%
Clarity	Clear
Solvent	Xylene
Oil Type	Soya Fatty Acids
Solid Content (% by wt)	60 +/- 1%
Viscosity (Gardner Scale@25°C)	Z1 - Z3
Acid Value	<15mg KOH/g
OH Value (on solids)	2.1 - 2.2 mg KOH/g
Color (Gardner)	5 max

### SOLUBILITY DATA

Aromatic - Esters	Complete
Miniral Spirits	Limited
Ethyl Cellosolve Acetate	Complete
2-Buthoxy Ethyl Acetate	Complete
Methyl Ethyl Ketone	Complete

### DELIVERY FORM DETAILS

Supplied as 60% in Xylene packed in mild steel drums (Net. weight 200KG)

### SHELF LIFE

Minimum 12 months when stored under standard storage conditions

#### DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.