

RARTPA TR-2606

FEATURES

High Gloss & Gloss retention, excellent color
 Medium Tg / good drying and forms hard and moderately flexible film.
 Excellent pigment wet ability and good resistance to detergents and soaps.

APPLICATIONS

As a decorative and quick drying paints. Industrial quality quick drying paints / as acrylic topcoat for textured paints. Road marking paints / for pavements / kerb stones / pathways.
 Clear lacquers for PVC leather cloth / over lacquering and Metallizing / coatings for electronic equipment like TV / video and similar items. Scratch resistant protective coats and polycarbonate glazing.

CHARACTERISTICS

Type of Resin	A composition of solution polymerization
Color/Clarity	Clear
Solvent	Xylene
Solids	60 +/- 1%
Viscosity(Gardner@25°C)	Z5 - Z6
Acid Value	< 15 mg KOH
Color (Gardner)	Water white (0.1 max in Gardner)

COMPATIBILITY DATA

Long Oil / Medium Oil / Styrenated Alkyd	Incompatible
Acrylic polyols	Limited
Cellulose esters	Good
Chlorinated rubber	Good
Vinyl resin	Good

SOLUBILITY DATA

Hydrocarbons	Xylene / Toluene: Soluble
Mineral Spirits	Limited
Alcohols	Soluble
Esters	Soluble
Ketones	Limited

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

DELIVERY FORM DETAILS (60% XYLENE)

Packing: 190 Kgs / net: 200 Lit Mild Steel Drums

SHELF LIFE

Minimum 12 months when stored under ambient storage conditions.

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM