

RARALKYD SA - 1608 XL

FEATURES

Excellent Gloss & Gloss retention, good color. High Viscosity.
High molecular weight, very good drying with good adhesion on many metallic substrates.
Good resistance to detergents and soaps.

APPLICATIONS

As a decorative and quick drying paints both as clear and pigmented systems.
Industrial quality OEM Quick drying primers and paints.
High quality finishes with various pigments .
Suggested also for Deeping system.

CHARACTERISTICS

Type of Resin	A copolymerized product of styrene monomer and selected monomers.
Clarity	Clear
Solvent	Xylene
Solids	60 +/- 1%
Viscosity(Gardner Tube @25 C)	70 +/- 5 Seconds
Acid Value	< 15 mg KOH
Color (Gardner)	5 max or Gardner
Touch dry	6 – 8 minutes
Dry to handle	Between 20 – 25 minutes with good recoat ability.

COMPATIBILITY DATA

Long Oil / Medium Oil / Short Oil Alkyd	Limited
Amino resins	Good
Chlorinated rubber	Good
Vinyl resin	Good

SOLUBILITY DATA

Hydrocarbons	Xylene / Toluene: Soluble
Mineral Spirits	Limited
Alcohols	Insoluble
Esters	complete

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

DELIVERY FORM DETAILS (60% XYLENE)

Packing: 190 Kgs / net: 200 Lit Mild Steel Drums

SHELF LIFE

Minimum 12 months when stored under ambient storage conditions.

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRRESIN.COM