

RARALKYD UA-15546 WS

FEATURES

- Very fast drying time
- Very Good abrasion resistance
- Light Color with good yellowing resistance
- Very Good compatibility with majority long and medium air dry alkyd resin

APPLICATION

- Varnish for parquet floor
- Furniture finishes and Yacht varnishes
- Wood varnishes
- Pigment decorative for interior use

CHARACTERISTICS

• Oil %	61%
• Type of Polyol	Penta
• Type of isocyanate	Aromatic isocyanate
• Free isocyanate content	0%
• Solvent	White Spirit
• Oil type	Soya bean oil
• Solid Content	55 +/- 2%
• Viscosity Gardner @25°C @55% WS	Z1-Z3
• Viscosity CP @25°C @55% WS	2700 - 4600
• Acid Value mg KOH/gm solid	2 max
• Color Gardner	5 max

SOLUBILITY DATA

Aliphatic hydrocarbon	Soluble
Aromatic	Soluble
Chlorinated	Soluble
Alcohols	Limited
Ketones	Soluble
Esters	Soluble
Glyco-Ethers	Soluble

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM

DELIVERY FORM DETAILS

It's available at 55% in White Spirit

STORAGE CONDITIONS

RARALKYD UA-15546 WS Should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures between 5°C and 30°C Exposure to sun shine should be avoided.

SHELF LIFE

Under the above mentioned storage conditions the stability of RARALKYD UA-15546 WS will be 12 months ex-work

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRRESIN.COM