

RARPOLYOL AP-1608 XL

FEATURES

Excellent fast drying.
 Very good weathering resistance.
 Excellent mechanical & adhesion properties.

APPLICATION

Two component car repair
 Suitable for galvanized steel & Aluminum substrates
 Protective coat

CHARACTERISTICS

Solvent	Xylene
Solid Content (% by wt)	60 ± 1%
Viscosity (Gardner Scale @ 25°C)	Z3 – Z4
Acid Value on solids (mg KOH/g)	2 – 5
% OH (on Solids)	0.9 – 1.1
Clarity	Clear
Color (Gardner 1933)	1 max

SOLUBILITY DATA

Aromatic Hydrocarbons	Soluble
Mineral Spirits	Insoluble
Ketones	Soluble
Esters	Soluble
Alcohols	Soluble

COMPATIBILITY DATA

Desmodur N75	Compatible
Desmodur L75	Compatible
Desmodur N3300	Compatible
NC 1/2 Sec	Limited

DELIVERY FORM DETAILS

Mild steel drums (Net .Weight 190 Kg)
 Minimum 12 months in original unopened containers stored between 5 and 35°C

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRRESIN.COM