

RARALKYD AR-37040 XL

FEATURES

- Excellent hardness excellent Gloss
- Excellent film leveling and fast solvent release properties
- Good sanding properties
- Excellent chemical resistance
- Recoat-ability and fast drying characteristics

APPLICATION

- General purpose for Industrial 2K
- Urethane two-components primers for metal, wood and aluminum substrates.
- Urethane two-components Matt & Gloss finishes and sealers with easy sandability
- NC sealers and Matt & Gloss top coat

CHARACTERISTICS

• Solvent	Xylene
• Solid Content	70+/-2%
• Viscosity Gardner @25°C @60% XL	Z3-Z4
• Viscosity CP @25°C @60% XL	4630 - 6340
• OH Content	3.0%
• Acid Value mg KOH/gm solid	10 max
• Color Gardner	6 max

SOLUBILITY DATA

Aliphatic hydrocarbon	Limited
Aromatic	Soluble
Chlorinated	Limited
Alcohols	Insoluble
Esters	Soluble
Ketons	Soluble
Glycol-Ethers	Soluble

COMPAIBILITY DATA

Medium oil Alkyd	Incompatible	Stand Oil	Limited
Short oil Alkyd	Compatible	Isocyanate	Compatible
Rosin maleate	Compatible	Urea/melamine resins	Compatible
Zinc White	Limited	Chlorinated rubber	Compatible
Red Lead	Incompatible		
NC	Compatible		

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

RARALKYD AR-37040 XL

DELIVERY FORM DETAILS

It's available at 70% Xylene

STORAGE CONDITIONS

RARALKYD AR 37040 XL Should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures between 5°C and 30°C Exposure to sun shine should be avoided.

SHELF LIFE

Under the above mentioned storage conditions the stability of RARALKYD AR 37040 XL will be 12 months ex-work