

RARESTER SP-1705 BA

FEATURES

Very good drying time with Isocyanates
Excellent film hardness and durability
Excellent glossy finishing and coverage

APPLICATION

Specially used for glossy PU topcoat coatings
Use with proper catalyst 50% or 100%

CHARACTERISTICS

Solvent	Butyl Acetate
Solids	70 +/- 1%
Hydroxyl value on solid	190 +/- 5
Viscosity (Gardner scale @ 25°C)	X - Z
Acid value	<12
Color (Gardner)	3 max

SOLUBILITY DATA

Aliphatic Solvents	Limited
Aromatic Solvents	Soluble
Terpenic Solvents	Limited
Ketones	Soluble
Esters	Limited

COMPATIBILITY DATA

Medium oil alkyd	Incompatible
Long oil alkyd	Incompatible
Rosin maleate	Incompatible

DELIVERY FORM DETAILS

70% in Butyl Acetate - Bulk
70% in Butyl Acetate - Drums (200kg/drum)

SHELF LIFE

Minimum 12 months when stored under standard storage conditions

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.