

## RARESTER UP-1756-HV

### FEATURES

Is a reactive and slight flexible unsaturated polyester resin  
Diluted in Styrene  
Have very hardness and good flow properties

### APPLICATIONS

Is mainly used in formulate clear wood coating  
Used for roller UV system and sealer with good sandability

### CHARACTERISTICS

Type of Resin	Unsaturated Polyester Resin
Color (Gardner) / Clarity	3 max
Monomer / Diluents	Styrene
Solids	75 +/- 1%
Viscosity(Gardner Tube@25°C)	Y - Z
Acid Value on Solids	30 - 40 mg/KOH
Gel Time	10 - 15 min @ 25°C

### COMPATIBILITY DATA

Acrylic Resins	Good
General Polyesters	Good

### SOLUBILITY DATA

Hydrocarbons	Xylene / Toluene: Soluble
Mineral Spirits	Limited
Alcohols	Insoluble
Esters	Complete

### DELIVERY FORM DETAILS

75% (Styrene)  
Packing: 220KG net: 200 Lit Mild Steel Drums

### SHELF LIFE

When stored in original containers at 25°C storage conditions can have a life of 6 months