

## RARESTER UP-1705-PS

### FEATURES

Is an unsaturated polyester resin  
Diluted in Styrene  
Have very good sandability, good reactivity and low greening

### APPLICATIONS

Is mainly used in sealer formulation, clear and pigmented

### CHARACTERISTICS

Type of Resin	Unsaturated Polyester Resin
Color (Gardner) / Clarity	3 max
Monomer / Diluents	Styrene
Solids	70 +/- 1%
Viscosity(Gardner Tube@25°C)	U - W
Acid Value on Solids	11-18 mg/KOH
Gel Time / Exothermic Peak	4 - 8 min @ 25°C

### COMPATIBILITY DATA

Acrylic Resins	Good
General Polyesters	Good

### SOLUBILITY DATA

Hydrocarbons	Xylene / Toluene: Soluble
Mineral Spirits	Limited
Alcohols	Insoluble
Esters	Complete

### DELIVERY FORM DETAILS

70% (Styrene)  
Packing: 220KG net: 200 Lit Mild Steel Drums

### SHELF LIFE

When stored in original containers at 25°C storage conditions can have a life of 6 months

#### DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.