

## RARALKYD MO-2555 WS

### FEATURES

Good gloss and good gloss retention  
 Good initial and through drying  
 Excellent flexibility and adhesion properties

### APPLICATION

Industrial air-drying paints  
 Structural steel paints, anticorrosive primers  
 Cement surface coat  
 Industrial machinery QD primers

### CHARACTERISTICS

Oil Length	50 %
Solids	55 +/- 1%
Solvent	WS
Oil type	SOFA
Color Gardner	4 max
Viscosity Gardner	Z6 - Z8
Acid Value on solids	15 max

### SOLUBILITY DATA

Aliphatic solvents	Soluble
Aromatic solvent	Soluble
Ketones	Soluble
Alcohols	Insoluble
Esters	Soluble

### COMPATIBILITY DATA

Medium Oil Alkyd	Compatible
Long oil Alkyds	Compatible
Rosin Oil Alkyds	Compatible

### DELIVERY FORM DETAILS

55% in White Spirit – Drums (185 kg / drum)

### SHELF LIFE

Minimum 12 months when stored under standard storage conditions

#### DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM