

RARALKYD MO-16046 WS

FEATURES

- Very Good Gloss & Gloss retention
- Very Good wetting properties for pigments & fillers
- Good yellowing resistance properties
- Very Good adhesion
- Light Color

APPLICATION

- Air dry metal primer and finishes
- Enamel undercoat
- Economical stoving enamel temp. 140°C to 160°C
- Interior & exterior decorative paints

CHARACTERISTICS

• Oil %	50%
• Type of Polyol	Mixed polyol
• Phthalic anhydride %	32%
• Solvent	White Spirit
• Oil type	Soya bean oil
• Solid Content	60 +/- 2%
• Viscosity Gardner @25°C @60% WS	Approx. Z6
• Viscosity Gardner @25°C @55% WS	Z3-Z4
• Viscosity CP @25°C @55% WS	Approx.4600
• Acid Value mg KOH/gm solid	10 max
• Color Gardner	5 max

SOLUBILITY DATA

Aliphatic solvents	Soluble
Aromatic solvent	Soluble
Chlorinated	Soluble
Alcohols	Limited
Ketones	Soluble
Esters	Soluble
Glyco-Ethers	Soluble

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

COMPATIBILITY DATA

Medium Oil Alkyd	Compatible
Long oil Alkyds	Compatible
Rosin Oil Alkyds	Compatible
Zinc White	Limited
Red Lead	Limited
NC	Incompatible
Chlorinated Rubber	Limited

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.