

RARALKYD L0-1709 WS

FEATURES

- Good gloss & gloss retention
- Good hardness & adhesion
- Excellent yellowing resistance

APPLICATION

- Interior & Exterior decorative paints
- High gloss enamel

CHARACTERISTICS

Oil type	Soya
Oil Length	55%
Solvent	White Spirit
Solid Content(% by wt)	70+/-1%
Viscosity (Gardner Scale@25 C)	>Z10
Viscosity (mPas@25 C)	140000 - 170000
Reduced Viscosity @ 40 % Solids	130 - 150 sec Ford Cup #4
Acid Value on solids (mg KOH/g)	8-12
Clarity	Clear
Color (Gardner 1933)	6 Max.

SOLUBILITY DATA

• Aromatic Hydrocarbons	Soluble
• Mineral Spirits	Soluble
• Ketones	Soluble
• Esters	Soluble
• Alcohols	Soluble

COMPATIBILITY DATA

Medium oil Alkyd	Compatible
Short Oil Alkyd	Incompatible

DELIVERY FORM DETAILS

Mild steel drums (Net .Weight 190 Kg)

SHELF LIFE

Minimum 12 months in original unopened containers stored between 5 and 35 C

DISCLAIMER:
The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM