

## **RARALKYD LO-1956 WS**

## **FEATURES**

- · High Brushability
- Good Gloss retention
- Good Adhesive & mechanical properties
- Good for different solvent dilution

#### **APPLICATION**

Decorative Enamel Paints for internal and external Applications

## **CHARACTERISTICS**

Oil Length 58%

Solvent White Spirit
Oil Type SOFA

Solid Content (% by wt) 90+/-1%

Viscosity(Gardner Scale,25°C) >Z6

Acid Value < 15 mg KOH/ g
OH value(on Solids) < 1.9 - 2.0 mg KOH/g

Color (Gardner@ 50%) 5 max

# SOLUBILITY DATA

Aliphatic Solvents
Alcohols
Esters
Ketones
Soluble
Soluble
Soluble
Soluble

# **COMPATIBILITY DATA**

Medium oil Alkyd Compatible
Short Oil Alkyd Incompatible
Rosin maleate Compatible

### **DELIVERY FORM DETAILS**

95% in White Spirit - Bulk & 95% in White Spirit - Drums (190 kg/drum)

## SHELF LIFE

Minimum 12 months when stored under standard storage conditions

#### DISCLAIMER

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.