

## RARALKYD LO-2706 WS

### FEATURES

High flexible use in enamel  
High Gloss retention, very good yellowing resistance  
Good mechanical properties  
Excellent Pigment Wet ability

### APPLICATION

• Decorative Enamel Paints for internal and external Applications

### CHARACTERISTICS

Oil Length	59%
Solvent	White Spirit
Oil Type	Soybean Oil
Solid Content ( % by wt)	70+/-1%
Viscosity(Gardner Scale,25°C)	>Z6
Acid Value	< 12 mg KOH/ g
OH value(on Solids)	1.9 - 2.0 mg KOH/g
Color (Gardner@ 50%)	5 max

### SOLUBILITY DATA

• Aliphatic Solvents	Soluble
• Alcohols	Soluble
• Esters	Soluble
• Ketones	Soluble

### COMPATIBILITY DATA

Medium oil Alkyd	Compatible
Short Oil Alkyd	Incompatible
Rosin maleate	Compatible

### DELIVERY FORM DETAILS

70% in White Spirit - Bulk & 70% in White Spirit - Drums (190 kg/drum)

### SHELF LIFE

Minimum 12 months when stored under standard storage conditions

DISCLAIMER:  
The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM