

## MALEIC ANHYDRIADE RESIN RC 130

### PROPERTY AND USAGE

They are used in paint widely, and have good admixture with nitro-cotton, they are applicable to produce nitrocellulose lacquer. The color of production is light and keeps good retention. On the other hand, they are used in ink and glossing paper.

### SPECIFICATIONS

Item	RC130
Appearance	Pale yellow, transparent with flakes
Color (Gardner grade)	2-4
Softening point ,°C	130+/-2
Acid value (mgKOH/g)	20-30
Impurities	<30ppm
Solubility in Benzene (1:1)	(Compatible, Clear)

### PACKAGE

In paper with plastic woven bags, 25kg net each; keep away from water and fire.

### OTHERS

We can produce RC-Resin in accordance with the technical target provide by user/customer.

**DISCLAIMER:**

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.