

RARACRYLIC 2004 X 50%

FEATURES

- Good quality polymer, Economical paint formulation.
- Very good application properties.
- Good water scrub resistance.
- Excellent shelf life and good durability.
- Miscible in water.

APPLICATION

RARACRYLIC 2004x50% used for wall paints for interior and exterior use on all surfaces with the exception of high alkaline substrates

THINNING DETAILS

Thinning is normally done with portable water to reduce the minimum film forming temperature (MFFT). Following coalescing agents are effective.

Butyl glycol acetate, butyl diglycol acetate and texanol.

To improve the freezing thaw stability, Ethylene glycol can be added. It should be added slowly and under continuous stirring to avoid the coagulation.

PROPERTIES

* VISCOSITY @ 25C	15000-20000 cps
*Density @20C	1.11 /cm3
pH	4-6
Residual monomer	0.5% max
Solid Content	50+/-1
MFFT	10C
Particle size	0.5nm

DELIVERY FORM DETAILS

Supply in 220kgs open top drums and 1 metric ton IBC.

DISCLAIMER:

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com W W W. R A R R E S I N. C O M

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.