

RARCYAN 60 HL

FEATURES

Weathering resistance (low yellowing)
 Fast drying
 Workability
 Solubility in Ketone (MEK and MIBK) and cellosolved acetate
 Restrict amounts of Toluene and Xylene may be used up to 20% on the total formular.

APPLICATION

Wood
 Metal
 Plastics

COMPOSITION

Type of Resin	HMDI/TDI TRIMER
Solvent	Ethyl Acetate, Butyl Acetate

SPECIFICATION

Non-Volatile (%)	60 +/- 1
Viscosity (Gardner)	E - H
Color (Hazen)	80 Max
NCO %	11 +/- 0.5
Free Monomer	1 Max

SOLUBILITY

White Spirit	Insoluble
Xylene	Limited
Toluene	Limited
Ethyl Acetate	Complete
MEK	Complete
Butyl Acetate	Complete

COMPATIBILITY * 1

CAB	Compatible
Nitro Cellulose	Compatible
Alkyd Polyol (A-814, AA-953-50)	Compatible
Polyester Polyol	Compatible
Acrylic Polyol	Compatible

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM

Safety: A material safety data sheet of the product is available on request.

Storage: The resin is sensitive to moisture and should be stored indoors in the original unopened and undamaged containers in a dry place at storage temperatures 5 & 25 Exposure to direct sunlight should be avoided. **SHELF LIFE:** Minimum 6 months when stored under the above ambient storage conditions.

DISCLAIMER:
The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM