

## RARCYAN 4075

### GENERAL DESCRIPTION

A variety of two-component Polyurethane Coating can be as a hardener.

### FEATURES

Weather resistance  
Flexibility

### APPLICATIONS

Automobile repair, Heavy duty protective coating  
Wood, Metal  
Plastic, Synthetic leather  
Adhesives, Film coating

### SPECIFICATION

PROPERTY	UNIT	VALUE
Non Volatile Content	-	74.0 - 76.0
Viscosity (25°C)	Gardner	E - H
NCO Content	%	16.2 - 16.8
Free Monomer	%	0.5 Max

### GUIDELINES FOR USE

Be sure to read the MSDS, Technical data and Warnings before using please.  
Likely to result in injury due to solvent vapors compressed, please be careful.  
Has the possibility change the viscosity of the product when stored for a long time.

**Storage:** After use, the remaining sealed to prevent moisture from entering the indoor storage, please.

#### References:

When used alone may be not cure.  
There is a possibility to be a compatibility problem when you use with another hardener.  
Mixed with the water-soluble resin used is the cause of the defects.

#### DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.