MATERIAL SAFETY DATA SHEET



RARCYAN 75N

1 IDENTIFICATION OF THE PRODUCT AND THE COMPANY

1.1 IDENTIFICATION OF THE SUBSTANCE:

IDENTITY (As used on label and list) : RARCYAN 75N

1.2 IDENTIFICATION OF THE COMPANY:

RAR Resin & Chemical Industries JLT

11th Floor, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE

2 COMPOSITION / INFORMATION ON INGREDIENTS

Hazardous Components (Specific Chemical Identity: Common Name(s))	OSHA PEL	ACGIH TLV	Other Limits Recommended	% (optional)	CAS NO.
Isocyanate Prepolymer	N/Av	N/Av	N/Av	75%	
Ethyl Acetate	N/Av	N/Av	N/Av	25%	141-78-6

3 PHYSICAL/ CHEMICAL CHARACTERISTICS

Boiling Point: 77.1 deg C (Ethyl acetate)

Flash Point : 4° C Specific Gravity ($H_2O=1$) : 1.08 Vapor Pressure (mm Hg) : unknown Melting Point : N/Av Vapor Density (AIR = 1) : 3.0 Evaporation Rate : -

Solubility in Water : Insoluble

Appearance and Odor : Clear, pale yellow liquid with characteristic odor.

4 FIRE FIGHTING MEASURES

Extinguishing Media : Dry Chemical, foam, water spray and CO₂

Special Fire Fighting Procedures: Liberation of Nitrous fumes by Thermal decomposition or

combustion

Unusual Fire and Explosion Hazards: When exposed to direct heat source, combustible vapor will generate,

which can explode when mixed with air and ignited

5 MEASURES IN CASE OF ACCIDENTS

Spillage / Leakage : Do not empty into drains. remove mechanically cover remainders with wet,

absorbent material (chemical binder \based on calcium silicate hydrate, sand) After approx. one hour transfer to waste container and do not seal. Keep damp in a safe

ventilated area for several days.

DISCLAIMER

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

6 HANDLING AND STORAGE

Handling: The operator should be trained in handling this product. When the drum is pressurized,

unscrew the bung slowly to release the pressure before taking it off. This product should not be filled in as unwashed or wet container.

The use of fire is strictly prohibited in the working area.

Those who show allergenic and sensitizing effects should not be in charge.

STORAGE: Keep container properly sealed and stored indoors in a well ventilated area.

Once opened, the container should be closed and sealed with nitrogen gas.

If stored outdoors, the container should be covered with waterproof canvas sheet to

avoid being exposed in the rain.

7 HAZARDS IDENTIFICATION

Health: The risk of concentration- dependent irritating effects on eyes, nose, throat and perspiratory.

Physical: The product reacted with water forming CO2 so container may rupture or explode

Eve contact: Irritation, blurred vision, damage

Ingestion: Vomiting, diarrhea, stomach pain, irregular heartbeat

Skin contact: Allergic reactions, skin disorders, rash

Inhalation: Depress central nervous system and results in stupor

8 FIRST AID MEASURE

In case of eye contact rinse carefully and thoroughly with water and seek medical advice. In case of skin contact wipe off mechanical and wash afflicted areas thoroughly with soap and plenty of water. In case of irritation of the respiration tract or swallowing, consult a doctor.

9 CONTROLS/ PERSONAL PROTECTION

Technical protection: Keep container dry and tightly closed in a cool and well ventilated place.

Avoide exposure to temperature above 50 °C. Ensure adequate ventilation

or exhaust ventilation in the working area.

Personal Protection: Wer suitable protective clothing, protective gloves, goggles/ mask

10 CHEMICAL REACTIVITY/ STABILITY

Chemical stability: Good stable (Avoid to high temperature and moisture)

Incompatibility: This product react with active hydrogen groups such as amines and alcohols

Decompostion: Reaction with water produces heat and carbon dioxide gas.

Polymerization : Polymerization by alkaline materials and amines.

11 INFORMATION ON TOXICITY

Acute toxicity : LD 50 oral : NO DATA

LC 50 inhalation : NO DATA

Not available

Subacute inhalation toxicity:

Chronic toxicity: Prolonged to the vapor or mist may reduce the function of the lungs.

Sensitizing effect on the skin may be chronic

Carcinogenic effect: No data on the effect on human beings (the IARC test)

DISCLAIMER

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

Mutagenic effect: No Data.

Irritation : Prolonged contact on the skin and eye will cause reddish swelling or severe pain

12 ECOLOGICAL INFORMATION

Biodegradability: Not availableBioaccumulation: Not availableFish toxicty: Not availableOther information on ecotoxicity: Not available

13 DISPOSAL COSIDERATIONS:

Disposal methods : Incinerate in an appropriate facility

Treat by authorized agents professionally trained in disposing

Industrial waste: Dispose after forming solid form through reaction with polyol

Handling : Empty drum should be left to stand with water and left to stand for 48 hours.

Water should subsequently be removed afterword

14 TRANSPORT INFORMATION

GGVSee / IMDG Code :	UN NO :	MFAG : EMS :
GGVE / GGVS : Class No		RID / ADR : Class No
ADNR: Class No	Cat	ICAO / IATA - DGR : NOT RESTR

Following all the regulations in your country

Perform under the supervision of an authorized operator

Other information Keep dry

Keep separated from foodstuffs

15 REGULATORY INFORMATION

Following all the regulations in your country

16 OTHER INFORMATION

Reason for issue: Update to new format Prepared: RAR Resin Technical Dept.