

RARCYAN 390N Non-Yellowing Hardener

FEATURES

390N is polyisocyanate with isocyanate ring and practically monomer free. These products give fully compatible with polyols, especially acrylic. They show a flexible coating and improved weather resistance.

Compatibility with polyol

Weather resistance

Fast Dry & Flexibility

APPLICATION

Automobile repair

Wood, metal, plastic and synthetic leather

Heavy duty protective coating

Adhesive

Film coating

CHARACTERISTICS

Type of Resin	HMDI TRIMER
Solvent	Butyl Acetate
Non-volatile (%)	89 - 91
Viscosity (Gardner)	M - Q
Color (Hazen)	80 max
NCO (%)	18.5 - 19.5
Free Monomer	0.5 Max

SOLUBILITY

White Spirit	Limited
Xylene	Complete
Toluene	Complete
Ethyl Acetate	Complete
Butyl Acetate	Complete

COMPATIBILITY DATA

CAB	Compatible
Nitro Cellulose	Compatible
Alkyd Polyol	Compatible
Polyester Polyol	Compatible
Acrylic Polyol	Compatible

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM

Packing: 220 Kgs net mild steel drums

Storage: The resin is sensitive to moisture and should be stored indoors in the original unopened and undamaged containers in a dry place at storage temperatures 5 & 25 Exposure to direct sunlight should be avoided. **SHELF LIFE:** Minimum 6 months when stored under the above ambient storage conditions.

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRRESIN.COM