

RARCYAN 75L

FEATURES

- RARCYAN-75L is used in combination with various materials containing hydroxyl groups for formulating Air-drying two component polyurethane coatings.
- Fast Drying
- Hardness
- Compatibility with polyol and solvent
- Solubility
- Cold-proof

APPLICATION

- Wood and metal finish
- Fabric and paper coating
- Coating on plastic rubber goods
- Adhesive for paper, synthetic leather and film & ink

CHARACTERISTICS

- | | |
|-----------------------|---------------|
| • Type of Resin | TDS ADDUCT |
| • Solvent | Ethyl Acetate |
| • Non-volatile (%) | 75 ± 1 |
| • Viscosity (Gardner) | V - Y |
| • Color (Gardner) | 1 max |
| • NCO (%) | 13 ± 0.5 |
| • Free monomer | 0.5 max |

SOLUBILITY

- | | |
|-----------------|----------|
| • White Spirit | Limited |
| • Xylene | Complete |
| • Butanol | Complete |
| • Butyl Acetate | Complete |
| • MEK | Complete |

COMPATIBILITY DATA

- | | |
|--------------------|------------|
| • Alkyd Polyol | Compatible |
| • Acrylic Polyol | Compatible |
| • Polyester Polyol | Compatible |

Packing: 220 Kgs net mild steel drums

STORAGE: The resin is sensitive to moisture and should be stored indoors in the original unopened and undamaged containers in a dry place at storage temperatures 5° & 25° Exposure to direct sunlight should be avoided.

SHELF LIFE: Minimum 6 months when stored under the above ambient storage conditions.

DISCLAIMER

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.