

## DIOCTYL PHTHALATE (DOP)

<b>SPECIFICATIONS</b>	<b>VALUE</b>	<b>RESULT</b>
Appearance		Clear Oily Liquid
APHA Color	Max. APHA	15
Refractive Index (25 Deg.C)	-	1.484
Specific Gravity D20	-	0.986
Water Content %	Max.	0.036
Volume Resistance (30 Deg. C)	Min.	$2.1 \times 10^{11}$
Acidity (KOH mg/g)	Max.	0.02
Volatility (%) (125 Deg. C 3hr.)	Max.	0.09
Acidity after heating	Max.	0.05
Ester Value		286
Purity	Min.	99.5%

**DISCLAIMER:**

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.