

## MALEIC ANHYDRIDE BRIQUETTE

PARAMETERS	STANDARDS	TEST RESULTS
PURITY	99.5% MIN	99.70%
MELTED COLOR	25 MAX	15
SOLIDIFICATION POINT	52.4 MIN	52.5
ASH CONTENT	0.005% MAX	0.00%
IRON CONTENT	5 PPM MAX	0.2 PPM