

Micronized Silica SS-SIL 270N

Test Item	Unit	Results	Specification		Test Method
			Min.	Max.	
Average Particle Size	μ	7.06	6.5	7.5	Malvern Master Sizer
Loss On Drying	Wt%	3.52	-	5.00	ISO 787-2
Oil Absorption	MI/100g	274	250	310	Linseed Oil
PH		7.11	6	8	In 5 Wt% Slurry
Wet screen residue, 325 Mesh through	Wt%	0.009		0.010	325 Mesh Screen
Whiteness		98	96		Hunter

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.