

MIDDLE CHROME

Product C.I. No: 77603

Volatiles at 100 degree C to 105 degree C	Max 1.0 %
Water Soluble matter	Max 1.0 %
Residue on 300 Mesh Sieve	Max 0.5 %
Oil Absorption value with R.L.O	25 - 30%
Specific gravity	5.1 - 5.4
Bulk Volume	Min 0.9 ml/gm
Hegman	6.5 - 7.0

Fastness

Acid	2
Alkali	1

Heat degree c 220

Bleeding Resistance

Water	5
Ethanol	5
Ethyle	5

Application

Air Drying Enamel
Industrial Paint

Light Fastness

Full Tone	5-6
Tint	5

Overspray 5

Xylene	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.