

CALCIUM OCTOATE 10%

SR NO.	Characteristics	Qualitative Specs		Quantative Specs			Unit	Inspection
		Test Results of Samples	Specs	Test Results of Samples	Specs of			
					Lower Limit	Upper Limit		Method
1	Appearance	Light Yellow Liquid	Light Yellow Liquid					Visual
2	Clarity	Clear	Clear					Visual
3	Non Volatile by Weight			73.76	75		%	120°C/hrs
4	Metal Content			35.97	35.5	36.5	%	Titration
5	Mt Tolerance	Soluble	To pass the test (1:19)					Visual
6	RLO Tolerance	Soluble	To pass the test (1:19)					Visual
7	Viscosity			72		80	sec.	F/C NO.4 @30°C
8	Film Appearance (Flooding on glass Panel)	Pass		0.985				Visual

DISCLAIMER:

The information contained in this datasheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about the product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.

11th Floor, 1 Lake Plaza, Jumeirah Lake Towers, P.O. Box: 47381, Dubai UAE | Tel: +971 4 4356517, +971 4 4356516 | Fax: +971 4 4356518, Email: info@rarresin.com

WWW.RARRESIN.COM