

LEAD OCTOATE 36%

PRODUCTS:

SR NO.	CHARATERISTICS	QUALITATIVE SPECS		QUANTITATIVE SPECS.			UNIT	INSPECTION	
		TEST RESULTS OF SAMPLES	SPECIFICATION Of	TEST RESULTS Of SAMPLES	SPECIFICATION of				METHOD
					LOWER LIMIT	UPPER LIMIT			
1	*Appearance	Light Yellow Liquid	Light Yellow liquid					Visual	
2	*Clarity	Clear	Clear					Visual	
3	*Non Volatile by Weight			73.76	75		%	120°C/hrs	
4	*Metal Content			35.97	35.5	36.5	%	Titration	
5	*Mt Tolerance	Soluble	To Pass the Test (1:19)					Visual	
6	*RLO Tolerance	Soluble	To Pass the Test (1:19)					Visual	
7	*Viscosity			72		80	sec.	F/C NO.4@30°C	
8	*Film Appearance (Flooding on glass panel)	Pass	To Pass the Test					Visual	

DISCLAIMER

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.